

GRACE ULTRA

Self-adhered roofing underlayment for high temperature applications

Product Description

Grace Ultra is composed of two waterproofing materials—an aggressive butyl rubber based adhesive backed by a layer of high density cross laminated polyethylene.

The product is 30 mils (0.76 mm) thick making it easy to handle and apply. The unique, advanced adhesive formulation offers premium adhesion to the roof deck, high quality laps, superior seal around roofing fasteners, and outstanding high temperature stability.

The adhesive is backed by a protective plastic release liner that protects its adhesive quality. The release liner is easily removed allowing the adhesive to be bonded tightly to the roof deck.

The membrane comes in a 198 ft² (18.4 m²) roll, and measures 34 in. (864 mm) wide.

Features & Benefits

Easy to handle and apply—The membrane bonds firmly to the roof deck and forms high quality laps.

Self sealing—The membrane meets key building code standards for nail sealability of self-adhered roofing underlayments.

Heat resistance—The membrane will resist elevated temperatures for extended periods of time without degradation of the adhesive.

Slip resistant surface—The slip resistant surface maximizes traction for safety without compromising the water integrity of the laps.

Plastic release—Plastic is easy to remove and easy to dispose of.

Aesthetically pleasing—The thin membrane meets code standards for fastener sealability but will not show through roof coverings.

Reroofable—Unlike some granular surfaced membranes, Grace Ultra will not adhere to the underside of the exposed roof covering making reroofing easier and less costly.

Grace expertise—Grace is the recognized leader in self-adhered roofing underlayments and is the manufacturer of Grace Ice & Water Shield®.



Guidelines for Use

Grace Ultra can be used as a sloped roof underlayment to help protect against leakage from water that builds up behind ice dams, or from wind-driven rain in applications where the membrane must withstand high in-service temperatures for extended periods of time.

High Temperature Applications

Grace Ultra is the appropriate product for all applications in hot desert southwest climates or any application where superior heat resistance is needed. In addition, Grace Ultra is the appropriate product for use under certain types of metal roofs (those employing copper, zinc, or Cor-Ten® panels). These metal roofs tend to readily conduct heat to the underlayment making them more likely to expose the membrane to high temperatures. It is up to the contractor and specifier to decide what level of performance is required based on the guidelines provided.


Wind-Driven Rain

Sloped roofs are not waterproof. They protect structures by shedding rain water. Storm-driven winds can cause sloped roof coverings to lift. Rain can be easily driven under the roof covering directly to the unprotected deck where it causes leaks and damage to the interior of the structure. Grace Ultra applied beneath the sloped roof covering helps prevent wind-driven rain from entering the structure. For wind-driven rain protection, full coverage with Grace Ultra is recommended. Since Grace Ultra is a vapor barrier, the roof construction must allow for proper ventilation in full roof coverage applications.

Ice Dams

For ice dam protection, Grace Ultra should be adhered at the edge of the roof deck by the eaves. The membrane should be applied to a point on the roof deck above the highest expected ice dam. Several variables influence the height of ice dams and the membrane coverage required. Local building codes should be consulted for specific requirements. Variables influencing the height of ice dams include climate (particularly the annual snowfall), slope, overhang, valleys, how well the structure is insulated and ventilated, and exposure (sun vs. shade). In addition to placement along the eaves, Grace Ultra can be used to help prevent roof leaks in a handful of danger zones like in valleys, at the rake edges, and around chimneys and skylights.

Use Grace Ultra on all of these critical areas



Installation Procedure

Surface Preparation

Install Grace Ultra directly on a clean, dry, continuous structural deck. Some suitable deck materials include plywood, wood composition, wood plank, metal, concrete, or gypsum sheathing. For all other substrates, contact your local Grace representative. Remove dust, dirt, loose nails, and old roofing materials. Protrusions from the deck area must be removed. Decks shall have no voids, damaged, or unsupported areas. Repair deck areas before installing the membrane.

Prime concrete, masonry surfaces and DensGlass Gold® with Perm-A-Barrier® WB Primer. Prime wood composition and gypsum sheathing with Perm-A-Barrier WB Primer if adhesion is found to be marginal (refer to Technical Letter 12, *Use on Oriented Strand Board (OSB) Roof Sheathing*). Apply Perm-A-Barrier WB Primer at a rate of 250–350 ft²/gal (6–8 m²/L). Priming is not required for other suitable surfaces provided that they are clean and dry.

Membrane Installation

Apply Grace Ultra in fair weather when the air, roof deck, and membrane are at temperatures of 40°F (5°C) or higher. Apply roof covering material at temperatures of 40°F (5°C) or higher.

Cut the membrane into 10–15 ft (3–5 m) lengths and reroll loosely. Tack/secure the end of the roll with a nail. Peel back 1–2 ft (300–600 mm) of release liner, align the membrane, and continue to peel the release liner from the membrane. Press the membrane in place with heavy hand pressure. Side laps must be a minimum of 3.5 in. (90 mm) and end laps a minimum of 6 in. (150 mm). For valley and ridge application,

peel the release liner, center the sheet over the valley or ridge, drape, and press it in place. Work from the center of the valley or ridge outward in each direction and start at the low point and work up the roof.

Alternatively, starting with a full roll of membrane, unroll a 3–6 ft (1–2 m) piece of membrane leaving the release liner in place. Align the membrane and roll in the intended direction of membrane application. Carefully cut the release liner on top of the roll in the cross direction being careful not to cut the membrane. Peel back about 6 in. (150 mm) of the release liner in the opposite direction of the intended membrane application exposing the black adhesive. Hold the release liner with one hand and pull the roll along the deck with the release liner, leaving the applied membrane behind. Use the other hand to apply pressure on the top of the roll. Stop frequently to press the membrane in place with heavy hand pressure. When finished with the roll go back to the beginning, reroll and pull the remaining release paper from the material, finishing the installation.

Consistent with good roofing practice, install the membrane such that all laps shed water. Always work from the low point to the high point of the roof. Apply the membrane in valleys before the membrane is applied to the eaves. Following placement along the eaves, continue application of the membrane up the roof. The membrane may be installed either vertically or horizontally.

Use smooth shank, electroplated galvanized nails for fastening shingles. Hand nailing generally provides a better seal than power-activated nailing. If nailing of the membrane is necessary on steep slopes during hot or extreme cold weather, backnail and cover the nails by overlapping with the next sheet.

Extend the membrane on the roof deck above the highest expected level of water back-up from ice dams and above the highest expected level of snow and ice on the wall sheathing on vertical side walls (dormers) and vertical front walls for ice dam protection. Consider a double layer of membrane in critical areas, such as along the eaves or in valleys and in climates where severe ice dams are anticipated. Apply the membrane to the entire roof deck for wind-driven rain protection. Apply a new layer of Grace Ultra directly over the old Grace underlayment in retrofit applications following the standard membrane application procedure.

Precautions & Limitations

- Slippery when wet or covered by frost.
- Consistent with good roofing practice, always wear fall protection when working on a roof deck.
- Release liners are slippery. Remove from work area immediately after membrane application.

- Do not leave permanently exposed to sunlight. Maximum recommended exposure is 60 days.
- Place metal drip edge or wood starter shingles over the membrane.
- Place metal drip edges or wood starter shingles over the membrane (refer to Technical Letter 15, *Roof Eave Application*).
- Do not fold over the roof edge unless the edge is protected by a drip edge, gutter, or other flashing material.
- Do not install on the chamfered edges of wood plank.
- Do not install directly on old roof coverings.
- Check with the manufacturer of the metal roofing system for any special requirements when used under metal roofing. Do not install directly under roof coverings especially sensitive to corrosion, such as zinc, without providing proper ventilation.
- Provide proper roof insulation and ventilation to help reduce ice dams and to minimize condensation. Grace Ultra is a vapor barrier.
- Repair holes, fishmouths, tears, and damage to membrane with a round patch of membrane extending past the damaged area 6 in. (150 mm) in all directions. If fasteners are removed leaving holes in the membrane, they must be patched. The membrane may not self-seal open fastener penetrations.
- Do not install fasteners through the membrane over unsupported areas of the structural deck, such as over the joints between adjacent structural panels.
- Due to its slight rubber-like odor, do not apply where the membrane is exposed to interior living space.
- Compatible with EPDMs (refer to Technical Letter 5, *Chemical Compatibility*). Also for use in tie-ins in EPDM with other Grace underlayments.
- Not compatible with polysulfides, flexible PVC or high concentrations of resin (pitch). For more information, refer to Technical Letter 5.

Standard Compliance

Grace Ultra meets the following standards:

- International Conference of Building Officials (ICBO) Report No. 3997
- Underwriters Laboratories, Inc. R13399 Class A fire classification under fiberglass shingles and Class C under organic felt shingles
- Underwriters Laboratories, Inc. Classified Sheathing Material Fire Resistance Classification Design Numbers P225, P227, P230, P237, P259, P508, P510, P512, P514, P701, P711, P717, P722, P723, P732, P734, P736, P742, P803, P814, P818, P824

Product Data

Roll length	70 ft (21.3 m)
Roll width	34 in. (864 mm)
Roll size	198 ft ² (18.4 m ²)
Packaging	Corrugated cartons
Roll weight	42 lbs (19.0 kg)
Rolls per pallet	25

Performance Properties

Property	Value	Test Method
Color	Gray-black	
Thickness, membrane	30 mil (0.76 mm)	ASTM D3767 method A
Tensile strength, membrane	250 psi (1720 kN/m ²)	ASTM D412 (Die C modified)
Elongation, membrane	250%	ASTM D412 (Die C modified)
Low temperature flexibility	Unaffected @ -20°F (-29°C)	ASTM D1970
Adhesion to plywood	3.0 lbs/in. width (525 N/m)	ASTM D903
Permeance (max)	0.05 Perms (2.9 ng/m ² s Pa)	ASTM E96
Material weight installed (max)	0.22 lb/ft ² (1.1 kg/m ²)	ASTM D461
Butyl based	Adhesive	

Grace Underlayments Product Selection Matrix

Waterproofing Membranes

Water-Shedding Membrane

Application Guidelines	Grace Ultra	Grace Ice & Water Shield®	Grace Select	Grace Basik®	Grace Tri-Flex 30®
Desert southwest United States	●	⊗	⊗	○*	●**
Under copper, zinc or Cor-Ten® in high altitude climates	●	⊗	⊗	⊗	⊗
Under architectural metal roofs	●	●	○	⊗	●
Roofing in high altitude/alpine regions	●	●	⊗	⊗	○***
Premium protection from severe ice dams	●	●	⊗	⊗	⊗
As a vapor barrier	●	●	●	○	○
As a temporary roof (see product specific appropriate exposure guidelines)	●	●	○	○	●

Note: When interpreting the above chart, consider that all Grace self-adhered underlayments, including Grace Ice & Water Shield, Grace Ultra, Grace Select and Grace Basik, are *waterproofing membranes*, while Grace Tri-Flex 30 provides a premium *water-shedding* roof protection.

* For application on wood substrates only

** White color only

*** White color is recommended

● Best ○ Good ⊗ Not Recommended

www.graceathome.com
www.graceconstruction.com

For technical assistance call toll free at 866-333-3SBM (3726)

Grace Ice & Water Shield, Grace Tri-Flex 30, Basik, Perm-A-Barrier, Vycor and Vycor Deck Protector are registered trademarks of W. R. Grace & Co.–Conn.

Cor-Ten is a registered trademark assigned to USX Corporation.

DensGlass Gold is a registered trademark of Georgia-Pacific Corporation.

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for the users' consideration, investigation and verification, but we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use which would infringe any patent or copyright. W. R. Grace & Co.–Conn., 62 Whittemore Avenue, Cambridge, MA 02140. In Canada, Grace Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This product may be covered by patents or patents pending.
 UL-005P Printed in U.S.A. 3/07

Copyright 2007. W. R. Grace & Co.–Conn.
 FA/LI/1M

GRACE